

# **Product Technical Data**

Features & Benefits:

100% Solids, No VOCs

Excellent immersion

resistance

# AM 2310 Grey Corrosion Protection

### **Product Description**

American Coatings' AM 2300 Corrosion Protection series consistently provides products of exceptional chemistry delivering the best in corrosion protection, while being safe for our environment and totally user friendly. Because our 2300 series is 100% solids, it contains no volatile organic compounds or solvents, and may be safely applied in confined areas with good ventilation

The 2300 series Coatings is the standard for lining ductile pipe used in the sewage and waste water industry and can be found protecting steel, ductile pipe and concrete substrates to a wide range of chemicals and solvents.

#### **Color:**

Gray

Container Size: 1 gallon kits

**Coverage per gallon (Theoretical):** 160 sq. ft. at 10 mils thickness

Flash Point:

>250°F (121°C)

#### Pull-Off Adhesion: Test ASTM D 4541 >2500 PSI

#### Recommended Thickness:

2 or 3 coats at 8–20 mils each, max vertical 12 mils

#### **Specific Gravity:**

Resin:	1.48
Hardener:	0.97

Volatile Organic Compounds (VOC): 0 grams/liter

#### Weight Per Gallon:

10.86 lbs, + / - .20

#### Specific Gravity:

40°F (4°C)	8 hours, 30 minutes
75°F (24°C)	45 minutes
75°F (24°C)	35 minutes

Note: Do not keep the blended coating in the original container unless immediate use is planned. Otherwise, exothermic heat cre $\neg$ ated during the curing process will considerably shorten the pot life. Pour the coating into a rolling tray or large aluminum-basting pan. Try to keep the depth of the coating in the tray below 3/8".

#### **Service Temperature:**

Dry Service	-30°F—250°F (121°C)
Spill/Splash	200°F (93°C)
*Immersion Service	170°F (76.7°C)

\* Water Immersion — 190°F (90°C) — Atlas test cell for 60 days, unaffected

#### **Pump Specifications:**

Pump Ratio	56:1 or greater
Minimum Output	5,600 PSI
Product Hose: Min.	
—Optimum I.D.	0.375–0.5 inch
Max. Length	60 feet
Tip Size	0.023-0.029

#### Cure Time (AT 70°F OR 21°C):

Re-coat Window Light Loading Immersion	24 hours maximum 2 days
(Aqueous) Service Full or Chemical	3 days
Service	7 days

## Multiple Coats:

Second and subsequent coats must be applied before the previous coat has completely cross-linked. If additional coats are needed after re-coat window, brush blast before applying the next coat. Small areas may be abraded by sanding or wire brushing.

The same requirements applies when overlapping the seams of adjacent coating sections to create a continuous protective film. If the coating surface to be overlapped at the seam cannot be brush blasted, use a non-impact means as power brushing or sanding to create a mechanical profile.

See reverse side for our liability and warranty.

### NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications.

NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANT-ABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFOR-MATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.