

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
ACETALDEHYDE	D	C	B	D	D	D	D	TD	C	C	C
ACETIC ACID 5%	D	D	B	D	D	D	D	D	D	D	D
ACETIC ACID 10%	B	B	A	C	C	B	B	B	C	C	C
ACETIC ACID 25%	B	B	A	C	C	B	B	B	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	D	C	B	D	D	D	D	D	C	C	C
ACETONE 10%	C	C	B	D	D	C	C	C	C	C	C
ACETONE 100%	C	C	B	C	C	C	C	C	C	C	C
ACETYL CHLORIDE	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
ACETONITRILE	D	C	B	D	D	D	D	D	C	C	C
ACRYLIC ACID	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
ACRYLONITRILE	TB	TB	A	TB	TB	TB	TB	TB	TB	TB	TB
ADIPIC ACID 25%	C	C	B	C	C	C	C	C	B	B	B
ALLYL ALCOHOL	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
ALLYL CHLORIDE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
ALUMINUM BROMIDE	D	D	C	E	E	D	D	D	D	D	D
ALUMINUM CHLORIDE	TD	TD	TC	TE	TE	TD	TD	TD	TD	TD	TD
ALUMINUM FLUORIDE	TD	TD	TC	TE	TE	TD	TD	TD	TD	TD	TD
ALUMINUM HYDROXIDE	D	D	C	E	E	D	D	D	D	D	D
ALUMINUM NITRATE	E	D	C	E	E	E	E	E	D	D	D
ALUMINUM SULFATE	D	D	C	E	E	D	D	D	D	D	D
AMMONIA	E	D	C	E	E	E	E	E	D	D	D
AMMONIUM CHLORIDE	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
AMMONIUM FLUORIDE	TC	TC	TB	TC	TC	TC	TC	TC	TC	TC	TC

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
AMMONIUM HYDROXIDE	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
AMMONIUM NITRATE	E	E	D	E	E	E	E	E	D	D	D
AMMONIUM OXALATE	D	D	TC	D	D	D	D	D	C	C	C
AMMONIUM NITRATE AMMONIUM PERSULFATE	TE	TD	TC	TE	TE	TE	TE	TE	TD	TD	TD
AMMONIUM PERSULFATE	D	C	B	E	E	D	D	D	C	C	C
AMMONIUM PHOSPHATE	D	C	B	E	E	D	D	D	C	C	C
AMMONIUM SULFATE	D	D	C	E	E	D	D	D	C	C	C
AMMONIUM SULFIDE	E	D	C	E	E	E	E	E	C	C	C
AMMONIUM SULFITE	E	D	C	E	E	E	E	E	C	C	C
AMYL ACETATE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
AMYL ALCOHOL	D	C	B	D	D	D	D	D	C	C	C
ANILINE	C	B	A	D	D	C	C	C	B	B	B
ANILINE HYDROCHLORIDE	C	B	A	D	D	C	C	C	B	B	B
ANTIMONY CHLORIDE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
AQUA REGIA	A	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
BARIUM ACETATE	D	C	B	E	E	D	D	D	D	D	D
BARIUM BROMIDE	D	C	B	E	E	D	D	D	C	C	C
BARIUM CARBONATE	D	C	B	E	E	D	D	D	C	C	C
BARIUM CHLORIDE	D	C	B	E	E	D	D	D	C	C	C
BARIUM HYDROXIDE	TD	TC	TB	TE	TE	TD	TD	TD	TD	TD	TD
BARIUM SULFATE	D	C	B	E	E	D	D	D	D	D	D
BARIUM SULFIDE	C	C	B	D	D	C	C	C	C	C	C
BENZYL CHLORIDE	TC	TC	A	TD	TD	TC	TC	TC	TC	TC	TC

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
BENZOIC ACID	C	C	B	D	D	C	C	C	C	C	C
BENZALDEHYDE	TC	TC	TB	TC	TC	TC	TC	TC	TC	TC	TC
BENZENE	TC	TC	TB	TD	TD	TC	TC	TC	TC	TC	TC
BENZYL ALCOHOL	E	D	C	E	E	E	E	E	D	D	D
BLACK LIQUOR (PAPER)	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
BLOOD SUGAR	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
BORAX	D	C	B	D	D	D	D	D	C	C	C
BORIC ACID	C	C	B	D	D	C	C	C	C	C	C
BRINE	E	D	D	E	E	E	E	E	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A	A
BUTANOL	E	D	C	E	E	E	E	E	D	D	D
BUTYL ACETATE	D	C	B	D	D	D	D	D	C	C	C
BUTYL ACRYLATE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
BUTYL AMINE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
BUTYL CARBITOL	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
BUTYL CELLOSOLVE	C	C	B	D	D	C	C	C	C	C	C
BUTYL ETHER	D	C	B	D	D	D	D	D	C	C	C
BUTYRIC ACID	B	B	A	C	C	B	B	B	B	B	B
CALCIUM BISULFITE	E	D	C	E	E	E	E	E	D	D	D
CALCIUM BROMIDE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
CALCIUM CARBONATE	D	C	B	D	D	D	D	D	C	C	C
CALCIUM CHLORATE	D	C	B	D	D	D	D	D	C	C	C
CALCIUM CHLORIDE	E	D	C	E	E	E	E	E	D	D	D
CALCIUM HYDROXIDE	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
CALCIUM HYPOCHLORITE	TC	TC	TB	TD	TD	TC	TC	TC	TC	TC	TC
CALCIUM NITRATE	E	E	D	E	E	E	E	E	D	D	D
CALCIUM SULFATE	C	C	B	D	D	C	C	C	C	C	C
CALCIUM SULFITE	C	C	B	D	D	C	C	C	C	C	C
CALCIUM DISULFIDE	B	B	A	C	C	B	B	B	C	C	C
CARBON TETRACHLORIDE	D	C	B	E	E	D	D	D	C	C	C
CASTOR OIL	D	C	B	E	E	D	D	D	C	C	C
CELLOSOLVE	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
CELLOSOLVE ACETATE	C	C	B	D	D	C	C	C	C	C	C
CHLOROACETIC ACID 25%	C	C	A	C	C	C	C	C	A	A	A
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	D	C	B	D	D	D	D	D	B	B	B
CHLOROFORM	TC	TB	A	TC	TC	TC	TC	TC	A	A	A
CHLOROPHENOL	A	A	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	TC	TC	A	TD	TD	TC	TC	TC	TB	TB	TB
CHROMIC ACID 10%	B	B	A	C	C	C	C	B	B	B	B
CHROMIC ACID 40%	B	B	A	B	B	B	B	B	A	A	A
CHROMIC CHLORIDE	B	B	A	B	B	B	B	B	A	A	A
CITRIC ACID	E	D	B	E	E	E	E	E	D	D	D
COPPER ACETATE	E	D	C	E	E	E	E	E	D	D	D
COPPER CHLORIDE	D	C	B	D	D	D	D	D	D	D	D
COPPER CYANIDE	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
COPPER NITRATE	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
COPPER SULFATE	D	C	B	D	D	D	D	D	B	B	B
CORN OIL	D	C	B	E	E	D	D	D	C	C	C
CORN STARCH SLURRY	E	E	E	E	E	E	E	E	E	E	E
CORN SUGAR	E	D	C	E	E	E	E	E	C	C	C
COTTONSEED OIL	D	C	B	E	E	D	D	D	C	C	C
CREOSOTE	D	C	B	E	E	D	D	D	C	C	C
CRESYLIC ACID	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
CUMENE	D	C	B	E	E	D	D	D	B	B	B
CUTTING OIL	D	C	B	E	E	D	D	D	C	C	C
CYCLOHEXANE	E	D	C	E	E	E	E	E	C	C	C
CYCLOHEXANONE	D	D	C	E	E	E	E	D	C	C	C
CYMENE	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
DETERGENTS ORGANIC	TD	TD	TC	TE	TE	TD	TD	TD	TC	TC	TC
DETERGENTS SULFONATED	TD	TD	TC	TE	TE	TD	TD	TD	TC	TC	TC
DEXTROSE	E	E	E	E	E	E	E	E	E	E	E
DIBUTYL PHTHALATE	E	D	C	E	E	E	E	E	D	D	D
DICHLORACETIC ACID	TB	TB	TB	TC	TC	TB	TB	TB	TB	TB	TB
DICHLOROETHANE	D	C	B	E	E	D	D	D	C	C	C
DICHLOROETHANE	C	B	A	C	C	C	C	C	A	A	A
DIESEL FUEL	D	C	B	D	D	D	D	D	B	B	B
DIETHANOLAMINE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
DIETHYL BENZENE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
DIETHYL KETONE	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
DIETHYLENE GLYCOL	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
DIETHYL ETHER	D	C	B	D	D	D	D	D	C	C	C
DIMETHYL ANILINE	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A	A
DIMETHYL SULFOXIDE	B	B	A	B	B	B	B	B	A	A	A
DINITRO BENZENE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
DINITRO TOLUENE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
EPOCHLOROHYDRIN	C	B	A	D	D	C	C	C	B	B	B
ETHANOL	C	C	B	C	C	C	C	C	C	C	C
ETHANOLAMINE	D	C	A	D	D	D	D	D	B	B	B
ETHYL ACETATE	C	B	A	C	C	C	C	C	B	B	B
ETHYL ACRYLATE	C	C	A	C	C	C	C	C	B	B	B
ETHYLAMINE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
ETHYL BENZENE	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
ETHYL BROMIDE	B	B	A	B	B	B	B	B	A	A	A
ETHYL CHLORIDE	B	B	A	B	B	B	B	B	A	A	A
ETHYL DICHLORIDE	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
ETHYLENE GLYCOL	E	D	C	E	E	E	E	E	D	D	D
ETHYL SULFATE	TD	TC	A	TD	TD	TD	TD	TD	TC	TC	TC
FATTY ACIDS	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
FERRIC CHLORIDE	E	E	D	E	E	E	E	E	D	D	D
FERRIC SULFATE	E	E	D	E	E	E	E	E	D	D	D
FERROUS NITRATE	E	E	B	E	E	E	E	E	C	C	C
FERROUS CHLORIDE	TD	TD	TC	TD	TD	TD	TD	TD	TD	TD	TD
FERROUS SULFATE	TE	TD	TD	TE	TE	TE	TE	TE	TD	TD	TD

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	D	C	B	E	E	D	D	D	B	B	B
FORMIC ACID 10%	D	C	A	D	D	D	D	D	B	B	B
FORMIC ACID 50%	B	C	A	B	B	B	B	B	A	A	A
FUEL OIL	E	D	B	E	E	E	E	E	B	B	B
FURFURAL ALCOHOL	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
GASOLINE AVIATION	D	D	C	D	D	D	D	D	C	C	C
GASOLINE DIESEL	D	D	C	D	D	D	D	D	C	C	C
GASOLINE JET FUEL	D	D	C	D	D	D	D	D	C	C	C
GASOLINE UNLEADED	E	D	C	E	E	E	E	E	C	C	C
GLUCOSE	E	E	D	E	E	E	E	E	D	D	D
GLYCERINE	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
GLYCOLIC ACID 70%	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
GREEN LIQUOR (PAPER)	E	D	B	E	E	E	E	E	C	C	C
HEPTANE	E	D	C	E	E	E	E	E	C	C	C
HEXANE	E	D	C	E	E	E	E	E	C	C	C
HYDRAULIC FLUID	E	D	B	E	E	E	E	E	C	C	C
HYDRAZINE 35%	TC	TB	A	TC	TC	TC	TC	TC	A	A	A
HYDRIODIC ACID 20%	D	C	A	D	D	D	D	D	B	B	B
HYDROBROMIC ACID 18%	C	B	A	C	C	C	C	C	B	B	B
HYDROBROMIC ACID 40%	TB	TB	A	TC	TC	TB	TB	TB	A	A	A
HYDROBROMIC ACID 60%	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
HYDROCHLORIC ACID 10%	D	D	C	D	D	D	D	D	D	D	D
HYDROCHLORIC ACID 36%	D	C	B	D	D	D	D	D	C	C	C

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	C	B	A	C	C	C	C	C	B	B	B
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	D	C	B	D	D	D	D	D	C	C	C
HYDROGEN SULFIDE 100%	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
ISOPHORONE	E	D	C	E	E	E	E	E	C	C	C
ISOPROPYL ACETATE	E	D	C	E	E	E	E	E	C	C	C
ISOPROPYL ALCOHOL	E	D	B	E	E	E	E	E	C	C	C
JET FUEL (JP-4)	D	D	C	D	D	D	D	D	C	C	C
KEROSENE	D	C	B	D	D	D	D	D	C	C	C
LACTIC ACID 10-20%	D	D	D	D	D	D	D	D	C	C	C
LACTIC ACID 50%	C	B	A	C	C	C	C	C	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	TD	TC	A	TD	TD	TD	TD	TD	TB	TB	TB
LEAD ACETATE	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
LEVULINIC ACID	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
LINSEED OIL	D	C	B	D	D	D	D	D	C	C	C
LITHIUM BROMIDE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
LITHIUM CHLORIDE SAT'D	D	C	B	D	D	D	D	D	B	B	B
LITHIUM HYDROXIDE	TC	TB	A	TD	TD	TC	TC	TC	TB	TB	TB
MAGNESIUM BISULFITE	D	C	B	D	D	D	D	D	C	C	C
MAGNESIUM CARBONATE	D	D	C	D	D	D	D	D	C	C	C

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
MAGNESIUM CHLORIDE	TC	TB	A	TC	TC	TC	TC	TC	TB	TB	TB
MAGNESIUM HYDROXIDE	C	C	B	C	C	C	C	C	B	B	B
MAGNESIUM NITRATE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
MAGNESIUM SULFATE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
MALEIC ACID	C	B	A	C	C	C	C	C	B	B	B
MANGANESE CHLORIDE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
MANGANESE SULFATE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
MERCURIC CHLORIDE	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
MERCUROUS CHLORIDE	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
METHANOL	C	B	B	C	C	C	C	C	B	B	B
METHYL ACETATE	C	B	A	C	C	C	C	C	B	B	B
METHYLAMYL ALCOHOL	TD	TD	TC	TD	TD	TD	TD	TD	TC	TC	TC
METHYL BENZOATE	D	C	B	D	D	D	D	D	C	C	C
METHYL CHLORIDE	B	B	A	B	B	B	B	B	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	C	B	A	C	C	C	C	C	A	A	A
METHYL ISOBUTYL KETONE	D	C	B	D	D	D	D	D	B	B	B
MILK	E	E	D	E	E	E	E	E	D	D	D
MOLASSES	E	E	E	E	E	E	E	E	D	D	D
MINERAL OILS	TE	TE	TD	TE	TE	TE	TE	TE	TD	TD	TD
MINERAL SPIRITS	D	D	C	D	D	D	D	D	C	C	C
MOTOR OIL	D	D	C	D	D	D	D	D	C	C	C
M-PYROL	A	A	A	B	B	A	A	A	A	A	A
NAPHTHA ALIPHATIC	E	D	B	E	E	E	E	E	C	C	C

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
NAPHTHA AROMATIC	D	C	A	E	E	D	D	D	B	B	B
NICKEL CHLORIDE	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
NICKEL NITRATE	D	C	B	D	D	D	D	D	C	C	C
NICKEL SULFATE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
NITRIC ACID 5%	E	D	C	E	E	E	E	E	D	D	D
NITRIC ACID 30%	C	C	B	C	C	C	C	C	C	C	C
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	TC	TC	TB	TC	TC	TC	TC	TC	TB	TB	TB
OIL SOUR CRUDE	E	D	C	E	E	E	E	E	C	C	C
OIL SWEET CRUDE	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
OLEIC ACID	D	C	B	D	D	D	D	D	B	B	B
OLEUM	B	B	A	C	C	B	B	B	A	A	A
OXALIC ACID	D	C	B	D	D	D	D	D	B	B	B
PERCHLORIC ACID	C	B	A	C	C	C	C	C	A	A	A
PERCHLOROETHYLENE	D	C	B	D	D	D	D	D	B	B	B
PHENOL 5%	C	B	A	C	C	C	C	C	A	A	A
PHENOL 85%	A	A	A	B	B	A	A	A	A	A	A
PHOSPHORIC ACID 40%	D	C	B	D	D	D	D	D	C	C	C
PHOSPHORIC ACID 85%	B	B	A	B	B	B	B	B	A	A	A
PICRIC ACID 10%	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
POTASSIUM ACETATE	E	D	C	E	E	E	E	E	D	D	D
POTASSIUM BROMIDE	E	D	D	E	E	E	E	E	D	D	D
POTASSIUM CARBONATE	E	D	D	E	E	E	E	E	D	D	D
POTASSIUM CHLORIDE	D	D	C	D	D	D	D	D	D	D	D

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
POTASSIUM HYDROXIDE 10%	E	D	C	E	E	E	E	E	D	D	D
POTASSIUM HYDROXIDE 50%	D	C	B	E	E	D	D	D	C	C	C
POTASSIUM IODIDE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
POTASSIUM NITRATE	E	D	C	E	E	E	E	E	D	D	D
POTASSIUM PERMANGANATE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
POTASSIUM PERSULFATE	D	C	B	D	D	D	D	D	C	C	C
POTASSIUM SULFATE	E	D	C	E	E	E	E	E	C	C	C
PROPIONIC ACID	C	B	A	C	C	C	C	C	A	A	A
PROPYLENE GLYCOL	E	D	D	E	E	E	E	E	D	D	D
PYRIDINE	A	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
SALT BRINE	E	D	C	E	E	E	E	E	D	D	D
SILVER NITRATE	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB
SKYDROL	C	C	C	C	C	C	C	C	C	C	C
SODIUM ACETATE	E	D	D	E	E	E	E	E	D	D	D
SODIUM BENZOATE	E	D	D	E	E	E	E	E	D	D	D
SODIUM BICARBONATE	E	D	D	E	E	E	E	E	D	D	D
SODIUM BISULFITE	TE	TD	TD	TD	TD	TD	TD	TE	TD	TD	TD
SODIUM BISULFATE	E	D	C	E	E	E	E	E	D	D	D
SODIUM CARBONATE	E	D	C	E	E	E	E	E	D	D	D
SODIUM CHLORATE 50%	TD	TD	TB	TD	TD	TD	TD	TD	TB	TB	TB
SODIUM CHLORIDE	E	D	C	E	E	E	E	E	C	C	C
SODIUM CHLORITE	D	C	B	D	D	D	D	D	B	B	B
SODIUM CHROMATE	D	C	B	D	D	D	D	D	B	B	B

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
SODIUM DICHROMATE	D	C	B	E	E	D	D	D	B	B	B
SODIUM FERROCYANIDE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
SODIUM FLUORIDE	TB	TB	A	TB	TB	TB	TB	TB	A	A	A
SODIUM HYDROXIDE 10%	E	E	C	E	E	E	E	E	D	D	D
SODIUM HYDROXIDE 50%	E	E	C	E	E	E	E	E	D	D	D
SODIUM HYPOCHLORITE 3%	D	D	A	D	D	D	D	D	B	B	B
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	E	E	D	E	E	E	E	E	D	D	D
SODIUM PEROXIDE	E	D	C	E	E	E	E	E	C	C	C
SODIUM PHOSPHATE 10%	E	D	C	E	E	E	E	E	C	C	C
SODIUM SILICATE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
SODIUM SULFATE	E	D	C	E	E	E	E	E	D	D	D
SODIUM SULFIDE	E	D	C	E	E	E	E	E	D	D	D
SODIUM SULFITE	E	E	D	E	E	E	E	E	D	D	D
SODIUM TARTRATE	E	D	C	E	E	E	E	E	D	D	D
SODIUM THIOSULFATE	E	D	C	E	E	E	E	E	C	C	C
STEARIC ACID	D	C	B	E	E	D	D	D	B	B	B
STYRENE	D	C	B	D	D	D	D	D	B	B	B
SULFAMIC ACID 25%	TC	TB	A	TD	TD	TC	TC	TC	A	A	A
SULFURIC ACID 10%	E	D	C	E	E	E	E	E	D	D	D
SULFURIC ACID 30%	D	C	C	D	D	D	D	D	C	C	C
SULFURIC ACID 98%	C	B	A	C	C	C	C	C	B	B	B
TALL OIL	E	D	C	E	E	E	E	E	C	C	C
TARTARIC ACID	TD	TC	TB	TD	TD	TD	TD	TD	TB	TB	TB

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART FOR NOVOLAC PRODUCTS



	AM253	AM254	AM255	AM256	AM256M	AM257	AM258	AM259	AM928	AM928 HV	AM929
A= NOT RECOMMENDED, B= SHORT TERM EXPOSURE/SPLASH SPILL, C= LONG TERM EXPOSURE/SPLASH SPILL, D= SHORT TERM IMMERSION, E= LONG TERM IMMERSION, *= HEAT CURE											
TETROCHLOROETHANE	D	C	B	D	D	D	D	D	B	B	B
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A	A
TOLUENE	D	C	B	D	D	D	D	D	C	C	C
TOLUENE SULFONIC ACID	D	C	B	D	D	D	D	D	B	B	B
TOLUIDENE	D	C	B	E	E	D	D	D	B	B	B
TRICHLOROACETIC ACID 20%	B	B	A	B	B	B	B	B	A	A	A
TRICHLOROETHANE	C	C	C	D	D	C	C	C	C	C	C
TRICHLOROETHYLENE	TC	TC	TB	TD	TD	TC	TC	TC	TB	TB	TB
TRICESYL PHOSPHATE	TD	TD	TB	TD	TD	TD	TD	TD	TB	TB	TB
TRISODIUM PHOSPHATE	E	D	C	E	E	E	E	E	C	C	C
TURPENTINE	D	D	B	D	D	D	D	D	C	C	C
UREA SOLUTIONS	TE	TD	TC	TE	TE	TE	TE	TE	TC	TC	TC
WHITE LIQUOR (PAPER)	TD	TC	TB	TE	TE	TD	TD	TD	TB	TB	TB
XYLENE	D	D	C	D	D	D	D	D	D	D	D
ZINC CHLORATE	TD	TC	TB	TD	TD	TD	TD	TD	TC	TC	TC
ZINC SULFATE	E	D	C	E	E	E	E	E	D	D	D

This data is provided as a service of American Coating Technologies and is believed to be accurate. However, this information is neither recommendations by American Coating Technologies nor product specifications. American Coating Technologies reserves the right to change or modify data as necessary.