



**american coating technologies**  
www.amcoating.com

## AM 1510 Severe Abrasion Resistance

### Product Description

AM 1510 has been engineered for areas where severe abrasion resistance with less than 24 mg loss on ASTM-D-4060 test. AM 1510 provides outstanding long term wear characteristics.

### Product Features and Benefits

- 100% Solids, No VOCs
- Long term wear protection
- Excellent abrasion resistance

### Chemical Resistance:

Acetic Acid up to 10%  
Ammonium Hydroxide 25%  
Brine Water  
Copper Sulfate  
Diesel Fuel  
Gasoline  
Hydrochloric Acid up to 30%  
Isopropyl Alcohol  
Mineral Spirits  
Potassium Hydroxide 50%  
Sodium Hydroxide 50%  
Sulfuric Acid 50%  
Sewage  
Alkalies  
Fresh and non-potable water

### Adhesion Strength:

ASTM D 4541 2,500

### Abrasion Resistance:

ASTM D4060 CS 17 Wheel 1000 Cycles 1KG  
23 MG

### Rockwell Hardness:

ASTM D 2240 80

### Compression Strength:

ASTM D 695 15,000psi

### Flexural Strength

ASTM D 790 13,000PSI

### Tensile Shear Strength:

ASTM D 1002 3,000PSI

### Color:

Dark Gray

### Container Size:

1 gallons

### Coverage per gallon (Theoretical):

160 sq. ft. @ 10 mils thickness

### Flash Point:

Greater than 250°F (121°C)

### Pull-Off Adhesion Test ASTM D 4541:

Minimum adhesion is 2550 psi

### Tabor Abrasion ASTM D 4060:

Greater than 24 mg (CS 17 Wheel Cycles:  
1KG load)

### Recommended Thickness:

2 coats @ 8-12 mils each

### Specific Gravity:

Resin: 1.48; Hardener: 1.02

### Volatile Organic Compounds (VOC):

0 grams/liter

### Weight per Gallon:

14.50 lbs

### Pot Life:

40°F (4°C)	8 hours 30 minutes
75°F (24°C)	2 hours 30 minutes
92°F (33°C)	55 minutes

### Cure Schedule @ 70°F or 21°C:

Recoat window	24 hours
Light Loading	2 days
Immersion (Aqueous) Service	3 days
Full or Chemical Service	7 days

### Service Temperature:

Dry Service	220°F (104°C)
Spill/Splash	180°F (82.2°C)
Immersion Service*	170°F (76.7°C)

\* Immersion with solvents, mineral acids, or alkalines, or if over 150°F contact factory

### Pump Specifications:

Pump Ratio	56:1 or greater
Minimum Output	5600 psi
Product Hose: Min.	
- Optimum I.D.	0.375 – 0.5 inch
Max. Length	50 feet

### Limitations:

Do not keep the blended coating in the original container unless immediate use is planned. Otherwise, exotherm—heat created during the curing process—will considerably shorten the pot life. Pour the coating into a rolling tray or large aluminum-basting pan. Try to keep the depth of the coating in the tray below 3/8".

See reverse side for application instructions.

See reverse side for limitations of our liability and warranty.

## AM 1510 Instructions:

**1) MULTIPLE COATS:** Second and subsequent coats must be applied before the previous coat has completely cross-linked. If additional coats are needed after re-coat window, brush blast before applying the next coat. Small areas may be abraded by sanding or wire brushing.

The same requirement applies when overlapping the seams of adjacent coating sections to create a continuous protective film. If the coating surface to be overlapped at the seam cannot be brush blasted, use a non-impact means as power brushing or sanding to create a mechanical profile.

**8) SAFETY:** Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and material safety data sheets before using. While all statements, technical information, and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user.

---

### NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

---

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for you particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications.

**NO WARRANTY IS MADE, EXPRESSED, OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABILITY OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sales of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW THE PRECAUTIONS TO PREVENT BODILY HARM.**